

FAST CURE 100% SOLID EPOXY PRIMER

DESCRIPTION

MAGIECHEM 5024 is fast cure two component 100% solid epoxy primer with very low viscosity and a very high penetration.
MAGIECHEM 5024 has an excellent wetting power of most substrates, which explains the excellent adhesion has been observed.
MAGIECHEM 5024 can be applied a cold condition as down as 2°C (36°F)

ADVANTAGE

- Excellent penetration.
- Low viscosity
- Good adhesion to concrete.
- Meets LEED requirement.

INSTALATION INSTRUCTIONS

The surface must be free from all contaminants such as grease, oil, tire marks Silicon and other.
Mechanical or chemical preparations are recommended, depending on surface and the conditions.

APPLICATION

Mix the material before use
Apply a stretch coat at the rate of 6-8mils (200 to 260 ft²/ US gal) with flat squeegee and back rolled.

PRECAUTIONS

- Consult MSDS before use.
- Can be applied down to 2°C (36°F).
- Apply on humid concrete up to 4.5%, or yellow-red scale according Delmhorst.



MAGIECHEM



FAST CURE 100% SOLID EPOXY PRIMER

QUALIFICATION AND QUANTIFICATION

Color: Clear, lightGrey, dark Grey and Beige

V.O.C.: ≤ 10 gr/liters (≤0.08 lbs /galUS)

Mix: 2 parts A and 1 part B in volume

Pot Life: 25 minutes for 0.5 kg (1.1lbs)

Application: Flat squeegee plus back -roll.

Recommended Thickness: 8-10 mils dry

Coverage: 200-260 ft²/ US gal

Recoat: 4-8 hours

Dry to touch: 3 hours

Complete cure: 7 days

Solvent Cleaner: MAGIECHEM 211

Shelf Life: 1 year in original unopened container

Packaging: 11.34L et 56.7 Litres (3 et 15 gal. US)

TECHNICAL SERVICES AND WARRANTY

For assistance, consult a representative of MAGIECHEM products.

The information contained in this data sheet is based on trials that we believe valid. However, when using, the conditions of application are beyond our control, the seller and / or the manufacturer disclaim any responsibility except to replace the product proves defective.



MAGIECHEM

SURFACE/GALLON					
Thickness (mils)	1	4	8	10	20
Gallon/sq.ft	1600	400	200	160	80

